JAIST Repository

https://dspace.jaist.ac.jp/

Title	Control of optical and mechanical properties of poly(methyl methacrylate) by introducing lithium salt
Author(s)	Ito, Asae; Maeno, Ryota; Yamaguchi, Masayuki
Citation	Optical Materials, 83: 152–156
Issue Date	2018-06-18
Туре	Journal Article
Text version	author
URL	http://hdl.handle.net/10119/16455
Rights	Copyright (C)2018, Elsevier. Licensed under the Creative Commons Attribution-NonCommercial- NoDerivatives 4.0 International license (CC BY- NC-ND 4.0). [http://creativecommons.org/licenses/by-nc- nd/4.0/] NOTICE: This is the author's version of a work accepted for publication by Elsevier. Asae Ito, Ryota Maeno, Masayuki Yamaguchi, Optical Materials, 83, 2018, 152-156, http://dx.doi.org/10.1016/j.optmat.2018.06.001
Description	



Control of optical and mechanical properties of poly(methyl methacrylate) by introducing lithium salt

Asae Ito, Ryota Maeno, Masayuki Yamaguchi*

School of Materials Science, Japan Advanced Institute of Science and Technology,

1-1 Asahidai, Nomi, Ishikawa 923-1292, JAPAN

*Corresponding author: Masayuki Yamaguchi Japan Advanced Institute of Science and Technology, 1-1 Asahidai, Nomi, Ishikawa 923-1292, JAPAN Phone: +81-761-51-1621; Fax: +81-761-51-1149; e-mail: m_yama@jaist.ac.jp

E-mail address

Asae Ito Ryota Maeno Masayuki Yamaguchi asae.ito@jaist.ac.jp s1610173@jaist.ac.jp m_yama@jaist.ac.jp

ABSTRACT

We investigated the effect of lithium trifluoromethanesulfonate (LiCF₃SO₃) on the optical properties of poly(methyl methacrylate) (PMMA), known as a glassy transparent polymer. The absolute values of the stress-optical coefficients in both the glassy and rubbery states were found to be reduced by the addition of LiCF₃SO₃. Furthermore, the linear coefficient of thermal expansion of the blend containing 10 wt.% of LiCF₃SO₃ was lower than that of pure PMMA, suggesting that the birefringence caused by thermal expansion in laminated display systems would be greatly reduced. These results indicate that PMMA/LiCF₃SO₃ is an appropriate blend for optical films used for liquid crystal displays.

Keywords: poly(methyl methacrylate); stress-optical coefficient; thermal expansion coefficient; dynamic mechanical property; birefringence

1. INTRODUCTION

Poly(methyl methacrylate) (PMMA) is a common plastic that is used for various optical applications, e.g., diffusing plates for liquid crystal displays (LCDs) [1-3], substrates for optical disks [4], and optical fibers [5, 6], owing to its high transparency. However, the heat resistance of PMMA is sometimes inadequate for such practical applications. Recently, we have succeeded in enhancing the glass transition temperature (T_g) of PMMA without losing transparency by adding lithium trifluoromethanesulfonate (LiCF₃SO₃) [7]. It has been reported that the T_g of PMMA can be enhanced by more than 40°C by the addition of 30 wt.% LiCF₃SO₃, making it comparable with that of polycarbonate [8, 9], which is another transparent plastic with high heat resistance. We believe that this improvement would be valuable to industry because it would solve one of the serious defects of PMMA. The $T_{\rm g}$ enhancement can be attributed to a reduction of segmental motion due to ion-dipole interactions between the lithium cations and the carbonyl groups in PMMA. Furthermore, the reduced segmental motion also affects the β -relaxation of the dynamic mechanical properties, which results in a high modulus in the glassy region, even near $T_{\rm g}$ [7]. This also contributes to the improved heat resistance, such as heat-distortion temperature.

The addition of low-molecular-weight compounds is known to have a marked effect on various optical properties, such as refractive index, stress-optical coefficient in the glassy region, and orientation birefringence [10-12]. Therefore, it has become a conventional method of modifying the optical properties of transparent plastics.

The addition of the salt does not affect the transparency, but the impact on other optical properties should be determined based on the relationship with the structure of the blends, which is the purpose of this study. It is well known that PMMA has a relatively

low refractive index [13]. Furthermore, the birefringence detected under applied stress in the glassy region is small, which is important for use in LCDs [13-15]. Further reduction of the photoelastic birefringence in the glassy region improves the quality of LCDs. Moreover, PMMA also has low orientation birefringence because its intrinsic birefringence is low [13, 16]. Further reduction of the orientation birefringence makes it possible to prepare a polarizer protective film by a conventional melt-extrusion process. We also evaluated the thermal expansion behavior of the blend, because strain caused by thermal expansion often causes unfavorable birefringence. Moreover, thermal warpage, caused by thermal expansion due to the heat generated from fluorescent lamps in backlight units [2], is a serious problem for PMMA-based diffusing plates in LCDs. Therefore, the suppression of thermal expansion is particularly important for large LCDs.

2. MATERIAL AND METHODS

2.1. Materials

PMMA (Acrypet VH) was kindly supplied by Mitsubishi Chemical Corporation (Tokyo, Japan). The number- and weight-average molecular weights—evaluated using size-exclusion chromatography (HLC-8020; Tosoh Corp., Tokyo, Japan) with chloroform as a solvent and polystyrene as a calibration standard —were $M_n = 54,000$ and $M_w = 120,000$, respectively. The lithium trifluoromethanesulfonate (LiCF₃SO₃ \geq 98.0%; Kanto Chemical Co., Inc., Tokyo, Japan) was used without further purification.

2.2. Methods

The PMMA and LiCF₃SO₃ were completely dissolved in a mixture of dichloromethane and methanol in a weight ratio of 9:1, and stirred for 1 h. The molar ratios of lithium ions to PMMA carbonyl groups were 0, 0.03, and 0.07, which

corresponded to 0, 5, and 10 wt.% of LiCF₃SO₃. The mixtures were cast in polytetrafluoroethylene-coated aluminum bats, dried in an air stream to volatilize the solvents, and further dried at 160°C for 30 h in a vacuum. The samples were then compression molded at 30 MPa for 10 min. After quenching at 25°C in a compression molding machine, we obtained 300-µm-thick films.

3. EXPERIMENTAL

3.1. Measurements

The temperature dependence of the dynamic mechanical properties was measured between room temperature and 200°C using a dynamic mechanical analyzer (Rheogel-E4000; UBM Co., Ltd., Muko, Japan) at 10 Hz. The heating rate was 2°C/min.

The refractive indices of the films with different salt contents were evaluated using an Abbe refractometer (DR-M2; Atago Co., Ltd., Tokyo, Japan) at 589 nm and room temperature. 1-Bromonaphthalene (purity 97%, refractive index 1.658; Sigma-Aldrich Co., Ltd., Dorset, UK) was used as a contact liquid.

The stress-strain curves were measured using a tensile machine equipped with a temperature controller (Rheogel-S1000; UBM Co., Ltd.,). The initial length of the rectangular films was 10 mm, and the draw ratio was 2. One of the chucks moved at a constant speed of 0.5 mm/s; i.e., the initial strain rate was 0.05 s⁻¹. The tensile test was performed at the temperature at which the tensile storage modulus at 10 Hz was 100 MPa. After hot-stretching, the sample was immediately cooled in an air stream and taken out. The retardation (R_e) was then measured at room temperature using a birefringence-measuring instrument (KOBRA-WPR; Oji Scientific Instruments Co., Ltd., Amagasaki, Japan) at 450, 498, 550, 589, 629, and 751 nm.

The photoelastic birefringence in the glassy region was evaluated using the birefringence-measuring instrument under various loads at room temperature.

The linear coefficient of thermal expansion was measured using a thermal mechanical analyzer (TMA4000SA, Bruker AXS Co., Ltd., Karlsruhe, Germany) in the temperature range 30–80°C. The tension load and heating rate were 20 kPa and 5°C/min, respectively.

4. THEORY/CALCULATION

Birefringence is represented by the sum of three contributions corresponding to their origins [17, 18]:

$$\Delta n = \Delta n_O + \Delta n_G + \Delta n_F \tag{1}$$

where Δn_0 , Δn_G , and Δn_F are the orientation birefringence, glassy photoelastic birefringence, and form birefringence, respectively. The first term derives from the orientation of the polymer chains caused by flow/deformation. The second component derives from the localized elastic deformation of the molecular chains in the glassy state. The third component derives from the anisotropic nano- and microstructures such as the array of nanostructured domains or lamellar structures. In the present report, the third term can be eliminated because the prepared samples were homogeneous. Therefore, we evaluated the effect of LiCF₃SO₃ on the orientation birefringence (Δn_0) and the photoelastic birefringence (Δn_G).

5. RESULTS AND DISCUSSION

5.1. Dynamic mechanical properties

The temperature dependence of the dynamic tensile properties of the samples with

various LiCF₃SO₃ concentrations is shown in Figure 1. The storage modulus *E'* decreased slightly in the glassy region and fell off sharply around at 120°C for pure PMMA, which is attributed to the glass-to-rubber transition, i.e., α -relaxation. Correspondingly, a distinct peak appeared in the tan δ curve in the temperature range of 120–160°C. Furthermore, a broad ambiguous tan δ peak, attributable to β -relaxation, was observed in the temperature range of 30–80°C for pure PMMA, which was indicated by the arrow. Although the relaxation is significantly weak, the mechanism was well studied by everal research groups [19-22]. According to them, this is owing to the local motion of the carbonyl side group having large dipole moment. It was also found from the figure that the LiCF₃SO₃ addition enhances *E'*. Moreover, its temperature dependence in the glassy region was reduced. The magnitude of tan δ in the glassy region became low, suggesting that β -relaxation is suppressed by LiCF₃SO₃. This is responsible for the high *E'* values in the glassy region.

[Fig. 1]

Moreover, the glass transition temperature (T_g) , defined as the peak temperature of α -relaxation in this study, increased with increasing the LiCF₃SO₃ content, as reported in our previous paper [7]. The hot-stretching temperature was determined from this measurement.

5.2. Refractive indices

The refractive indices at 589 nm of the blends are shown in Figure 2.

[Fig. 2]

Because the refractive index of LiCF₃SO₃ is low owing to the large amount of fluorine, the blends had lower refractive indices. In the case of transparent glassy plastics, such as PMMA, polycarbonate, and polystyrene, light transmittance as one of the most important properties for optical applications is mainly determined by the surface reflection. Therefore, the result in Figure 2 indicates that the surface reflection (r), given by the following equation [18], was reduced.

$$r = \frac{1 - n^2}{1 + n^2} \tag{2}$$

where n denotes the refractive index.

5.3. Orientation birefringence

The stress-strain curves obtained during film elongation are shown in Figure 3.

[Fig. 3]

As shown in the figure, the growth curves and the magnitude of the stress were almost the same for all the films, suggesting that the degree of molecular orientation, i.e., the orientation function, of the main chains was equal among these samples. The orientation birefringence (Δn_0) of each stretched film is shown in Figure 4.

[Fig. 4]

The orientation birefringence is provided by the following equation [17].

$$\Delta n_o = \Delta n^0 F \tag{3}$$

where *F* is the Hermans orientation function and Δn^0 is the intrinsic birefringence which is determined as follows;

$$\Delta n^{0} = \frac{2\pi}{9} \frac{\left(\overline{n}^{2} + 2\right)^{2}}{\overline{n}} N \Delta \alpha_{p}$$
(4)

where \overline{n} the average refractive index, N the number of molecules in unit volume, and $\Delta \alpha_p$ the polarizability anisotropy.

It is well known that PMMA has a small and negative intrinsic birefringence [13]. Therefore, we detected negative orientation birefringence. Furthermore, the wavelength dispersion was minimal because PMMA does not absorb strongly near the visible light region. As the LiCF₃SO₃ concentration increased, the absolute value of orientation birefringence decreased.

In a miscible blend comprising a polymer and a low-molecular-weight compound, orientation correlation—so-called nematic interaction—is expected during deformation/flow [23-28]. In other words, low-molecular-weight compounds orient to the deformation direction along with the polymer chains. Consequently, the optical anisotropy of the low-molecular-weight compound contributes to the total birefringence. Because the salt used in the present study, LiCF₃SO₃, has a positive intrinsic birefringence, the orientation birefringence increased to the positive direction (the absolute value of orientation birefringence decreased). In general, it is thought that the strength of the nematic interaction is enhanced when the molecular size of the lowmolecular-weight compound corresponds to the segment size of the host polymer [25-27]. In this system, however, the ion-dipole interaction with the carbonyl groups may induce the molecular orientation of LiCF₃SO. Moreover, another possibility should be considered: i.e., the ion-dipole interaction with the salt affects the polarizability anisotropy of PMMA. As shown in equation (4), when the ion-dipole interaction weakens the polarizability anisotropy of carbonyl groups, leading to a low intrinsic birefringence, the orientation birefringence decreases. Although the detailed mechanism is still unclear, the technique to reduce the orientation birefringence with the T_g enhancement will be attractive for PMMA to improve the quality of protective films.

5.4. Photoelastic birefringence

The stress-optical coefficient in the glassy region, which determines the photoelastic birefringence (Δn_G), is shown as a function of wavelength in Figure 5.

[Fig. 5]

The stress-optical coefficient of pure PMMA was approximately -4.3×10^{-12} Pa⁻¹, which corresponds with a previous report [29]. The result demonstrates that the photoelastic birefringence was reduced by LiCF₃SO₃. The reduced local motion of carbonyl side groups with large polarizability anisotropy, which is caused by ion–dipole interactions as shown in the β -relaxation mode, is responsible for the phenomenon. Although a recent study indicated that filling free volume by adding an antiplasticizer reduces the stressoptical coefficient in the glassy state [30], the salt addition would be another good method of reducing the photoelastic birefringence without losing mechanical toughness or heat resistance [7].

5.5. Linear thermal expansion

The linear coefficient of thermal expansion (α) is described by the following equation:

$$\alpha = \frac{1}{l_0} \left(\frac{dl}{dT} \right) \tag{4}$$

where l is the length. The temperature dependence of the linear thermal expansion coefficient is shown in Figure 6. In this figure, the average values of the linear expansion coefficient are plotted per 10°C.

[Fig. 6]

It was demonstrated that the thermal expansion is reduced by LiCF₃SO₃. Thermal

expansion often causes a problem in glassy polymers because the values are much larger than those of ceramics and metal [31]. In industry, inorganic fillers are added to reduce thermal expansion [32]. However, this technique is not applicable to optical films. Recently, an antiplasticized system with a low thermal expansion has been reported [25]. Although this seems to be an attractive method, the heat resistance and mechanical toughness were greatly reduced. Therefore, the present result should be noted, especially for optical applications such as laminated films with inorganic glass and polymer films with aluminum frames.

The coefficient of linear expansion of a metal is expressed by the anharmonic oscillatory behavior of lattice thermal vibration, generally described by the Lennard-Jones potential and so on. In the case of polymers, the coefficient of linear expansion depends on the skeletal vibrations of molecular chains. This can be explained using group interaction modeling (GIM) [33]. In other words, intermolecular vibration dominates the thermal expansion of a polymer. As the temperature rises, the anharmonicity caused by greater vibration increases the equilibrium intermolecular distance, resulting in positive thermal expansion. The addition of LiCF₃SO₃ restricts the molecular motion caused by ion–dipole interactions between carbonyl groups and lithium cations. The potential function consists of the sum of the attractive force and the repulsive force. Because the attractive force term is increased by introducing ion–dipole interactions, the minimum of the potential well of the intermolecular force deepens as a result of such strong intermolecular interactions. Therefore, the thermal expansion is reduced owing to the smaller equilibrium intermolecular distance caused by introducing ion–dipole interactions.

6. CONCLUSIONS

We evaluated the thermal and optical properties of PMMA/LiCF₃SO₃ blends. LiCF₃SO₃ decreased the orientation birefringence of films stretched at the same stress level. Because pure PMMA has a small intrinsic birefringence, the orientation birefringence of the blend was noticeably small. Furthermore, the photoelastic birefringence in the glassy state, i.e., the stress-optical coefficient, was reduced by the LiCF₃SO₃. We also found that the glassy region was extended into the high temperature range with reduced localized segmental motion, which may be attributed to the strong ion–dipole interactions between the lithium cations and the carbonyl groups of the PMMA. Such strong interactions are responsible for the small thermal expansion. The properties described above and the low refractive index of the PMMA blend make it an attractive choice for optical applications such as LCDs.

7. FUNDING SOURCES

A part of this work was supported by JSPS Grant-in-Aid for Scientific Research (B) Grant Number 16H04201.

8. REFERENCES

- G. Kim, A PMMA composite as an optical diffuser in a liquid crystal display backlighting unit (BLU), Eur. Polym. J. 41 (2005) 1729–1737.
- [2] C.H. Chien, C.C. Chen, T. Chen, Y.M. Lin, Y.C. Liu, Thermal deformation of microstructure diffuser plate in LED backlight unit, J. Soc. Inf. Disp. 24 (2016) 99– 109.
- [3] G.H. Kim, W.J. Kim, S.M. Kim, J.G. Son, Analysis of thermo-physical and optical

properties of a diffuser using PET/PC/PBT copolymer in LCD backlight units, Displays 26 (2005) 37–43.

- [4] N. Yamada, E. Ohno, K. Nishiuchi, N. Akahira, M. Takao, Rapid phase transitions of GeTe - Sb₂Te₃ pseudobinary amorphous thin films for an optical disk memory, J. Appl. Phys. 69 (1991) 2849–2856.
- [5] K. Kuriki, Y. Koike, Y. Okamoto, Plastic optical fiber lasers and amplifiers containing lanthanide complexes, Chem. Rev. 102 (2002) 2347–2356.
- [6] J. Zubia, J. Arrue, Plastic optical fibers: An introduction to their technological processes and applications, Opt. Fiber Technol. 7 (2001) 101–140.
- [7] A. Miyagawa, V. Ayerdurai, S. Nobukawa, M. Yamaguchi, Viscoelastic properties of poly(methyl methacrylate) with high glass transition temperature by lithium salt addition, J. Polym. Sci. Part B Polym. Phys. 54 (2016) 2388–2394.
- [8] N. Shamim, Y.P. Koh, S.L. Simon, G.B. McKenna, Glass transition temperature of thin polycarbonate films measured by flash differential scanning calorimetry, J. Polym. Sci. Part B Polym. Phys. 52 (2014) 1462–1468.
- [9] J. Brandrup, E.H. Immergut, E.A. Grulke, Polymer Handbook, fourth edi, Wiley Interscience, New York, 1999.
- [10] P. Kelly, A. Akelah, S. Qutubuddin, A. Moet, Reduction of residual stress in montmorillonite/epoxy compounds, J. Mater. Sci. 29 (1994) 2274–2280.
- [11] B. Ung, A. Dupuis, K. Stoeffler, C. Dubois, M. Skorobogatiy, High-refractive-index composite materials for terahertz waveguides: trade-off between index contrast and absorption loss, J. Opt. Soc. Am. B. 28 (2011) 917–921.
- [12] B.R. Hahn, J.H. Wendorff, Compensation method for zero birefringence in oriented

polymers, Polymer 26 (1985) 1619–1622.

- [13] S. Houran, A. Tagaya, Y. Koike, Mechanism of generation of photoelastic birefrengence in methacrylate polymers for optical devices, J. Polym. Sci. Part B Polym. Phys. 45 (2007) 1390–1398.
- [14] M. Yamazaki, Industrialization and application development of cyclo-olefin polymer, J. Mol. Catal. A Chem. 213 (2004) 81–87.
- [15] M. Schadt, Nematic liquid crystals and twisted-nematic LCDs, Liq. Cryst. 42 (2015) 646–652.
- [16] T.J. Hammack, R.D. Andrews, Temperature dependence of orientation birefringence of polymers in the glassy and rubbery states. II, J. Appl. Phys. 36 (1965) 3574–3581.
- [17] H. Shimada, S. Nobukawa, T. Hattori, M. Yamaguchi, Wavelength dispersion of birefringence of oriented polyethylene films, Appl. Opt. 56 (2017) 3806–3811.
- [18] M. Born, E. Wolf, Principle of optics: Electromagnetic Theory of Propagation, Interference and Diffraction of Light, Cambridge University Press, seventh ed., Cambridge, 1999.
- [19] E. Muzeau, J. Perez, G.P. Johari; Mechanical spectrometry of the beta-relaxation in poly(methyl methacrylate), Macromolecules 24 (1991) 4713–4723
- [20] K. Schmidt-Rohr, A.S. Kulik, H.W. Beckham, A. Ohlemacher, U. Pawelzik, C. Boeffel, H.W. Spiess, Molecular nature of the beta relaxation in poly(methyl methacrylate) investigated by multidimensional NMR, Macromolecules 27 (1994) 4733-4745.
- [21] F. Garwe, A. Schönhals, H. Lockwenz, M. Beiner, K. Schröter, E. Donth, Influence of cooperative α dynamics on local β relaxation during the development of the dynamic glass transition in poly(n-alkyl methacrylate)s, Macromolecules 29, (1996)

247-253.

- [22] W.J. Davis, R.A. Pethrick, Investigation of physical ageing in polymethylmethacrylate using positron annihilation, dielectric relaxation and dynamic mechanical thermal analysis, Polymer 39 (1998) 255-266.
- [23] M. Yamaguchi, M.E.A. Manaf, K. Songsurang, S. Nobukawa, Material design of retardation films with extraordinary wavelength dispersion of orientation birefringence: A review, Cellulose 19 (2012) 601–613.
- [24] M.E.A. Manaf, A. Miyagawa, S. Nobukawa, Y. Aoki, M. Yamaguchi, Incorporation of low-mass compound to alter the orientation birefringence in cellulose acetate propionate, Opt. Mater. 35 (2013) 1443–1448.
- [25] A. Miyagawa, S. Korkiatithaweechai, S. Nobukawa, M. Yamaguchi, Mechanical and optical properties of polycarbonate containing p-terphenyl, Ind. Eng. Chem. Res. 52 (2013) 5048–5053.
- [26] S. Nobukawa, H. Hayashi, H. Shimada, A. Kiyama, H. Yoshimura, Y. Tachikawa, M. Yamaguchi, Strong orientation correlation and optical anisotropy in blend of cellulose ester and poly(ethylene 2,6-naphthalate) oligomer, J. Appl. Polym. Sci. 131 (2014) 40570.
- [27] S. Nobukawa, Y. Aoki, Y. Fukui, A. Kiyama, H. Yoshimura, Y. Tachikawa, M. Yamaguchi, The effect of flexible chains on the orientation dynamics of small molecules dispersed in polymer films during stretching, Polym. J. 47 (2015) 294–301.
- [28] A. Kiyama, S. Nobukawa, M. Yamaguchi, Birefringence control of solution-cast film of cellulose triacetate, Opt. Mater. 72 (2017) 491–495.
- [29] A. Tagaya, H. Ohkita, T. Harada, K. Ishibashi, Y. Koike, Zero-birefringence optical

polymers, Macromolecules 39 (2006) 3019-3023.

- [30] S. Nobukawa, S. Hasunuma, T. Sako, A. Miyagawa, M. Yamaguchi, Reduced stressoptical coefficient of polycarbonate by antiplasticization, J. Polym. Sci. Part B Polym. Phys. 55 (2017) 1837–1842.
- [31] Y.S. Touloukian, Thermophysical Properties of Matter: Thermal Expansion of Nonmetallic Sollids, Plenum Press, New York, 1975.
- [32] L.E. Nielson, R.F. Landel, Mechanical Properties of Polymers and Composites, CRC Press, Boca Raton, 1994.
- [33] D. Porter, Group Interaction Modelling of Polymer Properties, Marcel Dekker, New York, 1995.

9. FIGURE CAPTIONS

- Figure 1 Temperature dependence of storage modulus E' and $tan \delta$ at 10 Hz for the blends with different LiCF₃SO₃ contents (0, 5, and 10 wt.%).
- Figure 2 Wavelength dispersion of refractive indices at 589 nm for PMMA/LiCF₃SO₃ blends at 25 °C.
- Figure 3 Stress-strain curves at hot-stretching for the blends with different LiCF₃SO₃ contents (0, 5, and 10 wt.%).
- Figure 4 Wavelength dispersion of orientation birefringence for the blends with different LiCF₃SO₃ contents (0, 5, and 10 wt.%).
- Figure 5 Wavelength dispersion of stress-optical coefficient in the glassy region for the blends with different LiCF₃SO₃ contents (0, 5, and 10 wt.%).
- Figure 6 Temperature dependence of linear coefficient of thermal expansion α for PMMA and PMMA/LiCF₃SO₃ (90/10).





Figure 2



Figure 3







Figure 6