JAIST Repository

https://dspace.jaist.ac.jp/

Title	高耐久性リチウムイオン二次電池用高分子化イオン液体バ インダー
Author(s)	PINDI JAYAKUMAR, TEJKIRAN
Citation	
Issue Date	2020-09
Туре	Thesis or Dissertation
Text version	ETD
URL	http://hdl.handle.net/10119/17011
Rights	
Description	Supervisor:松見 紀佳



Japan Advanced Institute of Science and Technology

Poly(ionic liquid) Based Binders for Highly Durable Li-ion Secondary Batteries.

Name: Pindi Jayakumar Tejkiran

Student number: S1720425

Name of the Lab: Matsumi Lab

Intended degree: Doctor of Science(Materials Science)

Research Content

The current thesis is based on the design and development of poly(ionic liquid) (PIL) based materials for Liion secondary battery (LiB) applications. Most of the commercial LiBs have graphite-based anodes. The performance and safety of these LiBs depend predominantly on the electrode-electrolyte interface, generally referred to as the solid electrolyte interface (SEI). Hence, it is very crucial to tune the SEI both compositionally and morphologically to enhance the performance of LiBs. PILs is a class of innovative polymers which combines the properties of ionic

liquids such as ionic conductivity. electrochemical and chemical stability and non-flammability with the mechanical toughness and processability of polymers. Ohno et al. have explored the use of PILs as in the energy application as electrolytes and have derived very promising results. Yuan et al. have reported the ability of the PIL to enhance the charge carrier ability at the electrode-electrolyte interface by creating a PIL/electrolyte heterojunction. This ability of PILs can be exploited to enhance the interfacial properties of the electrodes. The availability of a plethora of structurally diverse PILs allows for interfacial tuning to obtain the desired



Figure 1. Graphical abstract of the current research

properties. This thesis explores the interfacial tuning using PIL based binders and surface modification of the active material by PILs as shown in Figure 1. The relation of PIL structure vis-à-vis its performance has been investigated to understand the role of the substituent and the counter-ion.

Chapter 2: Allylimidazolium Based Poly(ionic liquid) Anodic Binder for Lithium-ion Batteries with Enhanced Cyclability.

In this chapter, the design and synthesis of an allylimidazolium based PIL as a binder for graphite anode were carried out. Engineering the structure and HOMO-LUMO levels of the binder is very crucial in tuning its properties. Though the binder constitutes a very small fraction of the gravimetric weight of the electrode, it can have a great effect on the performance of the LiB. Poly(vinylbenzylallylimidazolium bis(trifluoromethane)sulfonylimide) (PVBCAImTFSI) comprising an imidazole heterocycle and allyl substituent (Figure 2) was used as a binder for graphite anodes in lithium-ion batteries. DFT based theoretical studies





also speculated the suppression in the electrolyte degradation in the case of PVBCAImTFSI binder due to the positioning of its HOMO-LUMO levels as compared to the electrolyte. As predicted, anodes with the PVBCAImTFSI

binder exhibited lesser electrolyte degradation, decrease in intercalation-deintercalation, over potential and higher lithium-ion diffusion. Electrochemical Impedance Spectroscopy (EIS) results showed decreased interfacial and diffusion resistance for PVBCAImTFSI based electrodes after cycling. Dynamic Electrochemical Impedance Spectroscopy (DEIS) results indicated that the SEI resistance for the PVBCAImTFSI based anodes to be three times lesser than the PVDF based anodes. A reversible discharge capacity of 210 mAh/g was obtained for PVBCAImTFSI based half-cells at 1C rate as compared to the 140 mAh/g obtained for PVDF based anodic half-cells. After 500 cycles, 95% retention in the discharge capacity was observed. Also, PVBCAImTFSI based anodes exhibited better charge-discharge stability than the PVDF based anodes. Suppression of electrolyte degradation, reduction in the interfacial resistance, enhanced wettability and optimal SEI layer formed in the



Figure 3. Graphical abstract of the functioning of PVBCAImTFSI binder

case of PVBCAImTFSI based anodes cumulatively led to enhanced stability and cyclability during the chargedischarge studies as compared to the commercially employed PVDF based anodes. Thus, the tuning of the interfacial properties leads to the improvement in the performance of the lithium-ion batteries with PVBCAImTFSI as a binder. A graphical representation of the functioning of the binder is shown in Figure 3. However, it is crucial to understand the effect of the substituent and the counter-ion on the PIL vis-à-vis its performance as a binder. This is investigated in the next chapter by evaluating the performance of the PILs with different substituent and counter-ion.

Chapter 3: Effect of the PIL Binder Structure on the Performance of the Lithium-ion Batteries.

Two structurally varying poly(ionic liquid)s were synthesized to understand the effect of the PIL structure on its performance as a binder in LiBs. This will help in the tuning of the polymer structure to optimize its performance in LiBs. The properties of ionic liquids such as ion conductivity, glass transition temperature, viscosity etc. can be tuned by a simple modification of the sidechain or changing the counter-ion. Sidechains such as allyl group increases the ionic conductivity and decreases the viscosity of the ionic liquids. Counter-ions especially FSI assists in the formation of a better electrodeelectrolyte interface. Therefore, in this study, the design of PILs was carried such that one of the PILs PVBCAImFSI contain both the allyl side-chain and FSI anion. The other PIL PVBCBImTFSI has an alkyl chain and TFSI anion. Cyclic voltammetry studies indicated a suppressed electrolyte degradation for



Figure 4. Graphical abstract showing the effect of tuning of PIL structure on its performance

PVBCAImFSI based anodes leading to the formation of a better interface. This was supported by the DEIS measurements whose results indicated lesser R_{SEI} values for the PVBCAImFSI based anodes. Also, the lithium-ion diffusion kinetics was found to be better in these electrodes. The charge-discharge measurements were carried out to evaluate the durability and stability of the electrodes. Half-cells with PVBCAImFSI based graphite anodes showed enhanced durability up to 1500 cycles with a 60% capacity retention. By changing the TFSI anion to FSI in

PVBCAImTFSI, a 400% increase in capacity retention was observed after 1500 cycles. Whereas PVBCBImTFSI based LiBs showed lower capacities with lesser durability. The current study highlights the importance of the side-chain and the counter-ion present on the PIL vis-à-vis its performance as a binder in LiBs as shown in Figure 4.

Chapter 4: Surface Tethered Poly(ionic liquid) for Silicon Nanoparticles in Li-ion Battery Composite Anodes.

The above results show the ability of the PILs to tune the electrode-electrolyte interfacial properties. This led us further to design surface-modified silicon nanoparticles for composite anodes to obtain higher capacities than the conventional graphite anodes. In this chapter, poly(ionic liquid) (PIL) tethered silicon nanoparticles were investigated (Figure 5) as active material in combination with graphite for lithium-ion battery composite anodes. The results obtained are encouraging and calls for more optimization of functionalization and PIL structure. Silicon falls into the category of high energy density materials with a gravimetric energy density of over 4000 mAh/g, has immense potential to plug the current energy demand. However, due to the inherent volumetric changes researchers have failed

in many attempts to commercialize silicon anode based lithium-ion batteries. Formation of a passivation layer (SEI) at the electrode-electrolyte interface is very crucial in preventing the damage to the electrode in the harsh cycling conditions. An ideal SEI layer must be ionically conductive and electronically non-conducting. The PILs are known to possess good ionic conductivity and can act as interface enhancing agents to design a better interface. In this work, PIL functionalized silicon nanoparticles were prepared by esterification of poly[1-(5carboxypentyl)-3-vinyl-1H-

imidazol-3-ium bromide] with hydroxyl functionalized silicon



Figure 5. Summary of Surface Tethered Poly(ionic liquid) for Silicon Nanoparticles for LiB anodes

nanoparticles. Cyclic voltammetry studies of PIL functionalized silicon nanoparticles based composite anodes indicated an increase in the lithiation-delithiation currents with the cycling. They also exhibited a very high lithiumion diffusion coefficient of about $1.01*10^{-8}$ cm/s which indicated a robust and conducive SEI formation. These electrodes exhibited about 735 mAh/g of reversible discharge capacity after 34 cycles. This chapter presents preliminary results and performance of the anodes can be improved by more fine-tuning of the PIL structure and functionalization.

Keywords: Poly(ionic liquid)s, lithium-ion batteries, graphite anodes, binders, interfacial tuning, surface-functionalized silicon nanoparticles, structure-activity relationship.