## **JAIST Repository**

https://dspace.jaist.ac.jp/

| Title        | バイオベース窒素ドープカーボンにCoFe2O4ナノ粒子を担持させたリチウム空気電池用両機能性電気化学触媒 |
|--------------|--|
| Author(s)    | Pirapath, Arkasalerks                                |
| Citation     |  |
| Issue Date   | 2024-09  |
| Туре         | Thesis or Dissertation                               |
| Text version | ETD  |
| URL          | http://hdl.handle.net/10119/19396                    |
| Rights       |  |
| Description  | Supervisor: 松見 紀佳, 先端科学技術研究科, 博士                     |



名 氏 PIRAPATH ARKASALERKS 学 類 博士(マテリアルサイエンス) 位 0 種 学 位 記 番 博材第 585 号 묽 位授 与 年 月 日 令和6年9月 24 日 CoFe<sub>2</sub>O<sub>4</sub> Nanoparticles on Bio-based Polymer Derived Nitrogen 文 題 論 目 Doped Carbon as Bifunctional Electrocatalyst for Li-air Battery 論 北陸先端科学技術大学院大学 文 審 査 委 員 松見 紀佳 教授 純平 同 准教授 上田 西村 俊 同 准教授 HO Anh Van 同 准教授 兵庫県立大学 柿部 剛史 准教授

## 論文の内容の要旨

This research work focuses on the utilization of a bio-based polymer-derived nitrogen-doped carbon as a support for CoFe<sub>2</sub>O<sub>4</sub> nanoparticles electrocatalyst in Li-air battery application. This work also showcases the electrocatalyst's bifunctional ability to perform robust electrochemical performances. Nowadays lithium-air batteries (LABs) have emerged as a promising prospect due to their unparalleled theoretical energy density of 3,505 Whkg<sup>-1</sup>. However, despite the promising theoretical advantages, issues such as poor cycling stability, limited lifespan, and unresolved side reactions have hindered their commercial viability and widespread adoption. The major challenges of LABs are sluggish oxygen kinetics from oxygen reduction reaction (ORR) and oxygen evolution reaction (OER) are major issues that hinder their performance. Hence, developing electrocatalysts to promote ORR/OER is essential to reach the theoretical performance of LABs.

In this study, we introduced spinel cobalt iron oxide (CoFe<sub>2</sub>O<sub>4</sub>) nanoparticles decorated on bio-derived pyrolyzed poly(2,5-benzimidazole) (PYPBI800) as a nitrogen-doped carbon support electrocatalyst for LABs. The electrocatalyst was synthesized through pyrolysis of PBI followed by incipient wetness impregnation calcination on the metal precursors. The Strong Metal-Substrate Interaction (SMSI) between CoFe<sub>2</sub>O<sub>4</sub> and PBI800 has been confirmed with X-ray photoelectron spectroscopy. Due to both the intrinsic properties of CoFe<sub>2</sub>O<sub>4</sub> and the nitrogen doping effect, these electrocatalysts also modulate the electronic state of metals, facilitating oxygen adsorption and desorption at the electrode.

The electrocatalysts were evaluated as air-breathing electrodes in a CR-2032 coin-type cell LABs compared with other types of carbon supports. The initial discharge capacity for LAB coin cells with CoFe<sub>2</sub>O<sub>4</sub> on PBI800 was observed to be 18,356 mAhg<sup>-1</sup>. Furthermore, the cycling stability of the CoFe<sub>2</sub>O<sub>4</sub> on PBI800 cathode was tested through 200 charge-discharge cycles at 400 mAg<sup>-1</sup> with 1,000 mAhg<sup>-1</sup> cut-off capacity. The resulting cycle-life data revealed that the battery maintains a discharge capacity as high as 100% even after the 200th cycle, demonstrating exceptional stability with overpotential remains consistently low at 140 mV throughout the examined cycle. The extensive surface area with N

heteroatom defects of the PBI provides abundant nucleation sites for CoFe<sub>2</sub>O<sub>4</sub> nanoparticles which serve as active sites for ORR and OER. The CoFe<sub>2</sub>O<sub>4</sub> nanoparticles formed on the support exhibit strong metal-substrates interaction which leads to high exceptional stability and electrocatalytic activity.

Based on these findings, the CoFe<sub>2</sub>O<sub>4</sub> nanoparticles on bio-based polymer-derived nitrogen-doped carbon suggested through this hold promise as a practical air-breathing electrode for high-performance rechargeable LABs. This work will also benefit future heteroatom-doped carbon support design, specifically nitrogen to enhance LABs performance.

**Keywords:** Oxygen Reduction Reaction, Oxygen Evolution Reaction, Metal Nanoparticles, Lithium Air Battery, Nitrogen Doped Carbon.

## 論文審査の結果の要旨

リチウム空気電池は、カソード側における酸素還元反応とアノード側におけるリチウムの酸化反応により 放電が行われる高エネルギー密度蓄電池であり、重量エネルギー密度はリチウムイオン二次電池のそれを 大幅に上回ることから、次世代用用途において期待されている。一方で、それらの実効的な性能をさらに 改善しつつ、耐久性を高めていく上で課題も山積している。例えば、電気化学触媒自体の性能に加えて、 放電によって生成する  $\text{Li}_2\text{O}_2$  を酸素発生反応(充電反応)が起こるまでカソード側の細孔に保持できる ようなモルフォロジー的な条件も求められる。

本研究においては、電気化学触媒である  $CoFe_2O_4$  との強い SMSI (Strong metal-substrate interaction; 強い金属—基板相互作用) が期待できる高濃度窒素ドープカーボンを支持体として採用した。 $CoFe_2O_4$  と高濃度窒素ドープカーボンから成るコンポジット電極材料を HRTEM や XPS 等によりキャラクタライズした。

三電極系において、酸素還元反応と酸素発生反応の反応性をそれぞれ評価したところ、いずれの反応においても貴金属触媒系に匹敵する高活性を示していることが明らかとなった。とりわけ、高濃度窒素ドープカーボンの窒素のコバルトへの配位が酸素還元反応への活性を高めたと考えられる。同時に、高濃度窒素ドープカーボンのメソポーラスな特性が  $\text{Li}_2O_2$  に担持サイトを提供した。

実際にリチウム空気電池セル(コインセル)を構築し、酸素雰囲気下における充放電挙動を検討したところ、 $400~\rm mAg^{-1}$  の電流密度(充放電速度)において  $18,356~\rm mAhg^{-1}$ (触媒重量当たり)の高容量を観測するに至り、 $200~\rm theorem$  サイクルにわたって安定な充放電挙動を示した。また、オーバーポテンシャルも  $140~\rm mV$  と低く、スムーズな電気化学反応を示唆した。

本研究はバイオベースポリマーであるポリベンズイミダゾールから誘導した高濃度窒素ドープカーボンを卑金属系電気化学触媒である  $CoFe_2O_4$  の活性化に応用した最初の研究であるのみでなく、貴金属系電気化学触媒に匹敵するパフォーマンスを酸素還元反応(放電反応)と酸素発生反応(充電反応)の双方において示している点において、学術的、実学的に共に興味深い。その結果として、実電池セルにおいても可逆的に高い放電容量を発現するに至っており、今後のリチウム空気電池設計においても有益な設計指針を与えていると考えられる。

以上の理由から、本論文は博士学位論文としての価値を十分に有するものと認める。