JAIST Repository

https://dspace.jaist.ac.jp/

Title	C_<70> Molecular Stumbling inside Single-Walled Carbon Nanotubes			
Author(s)	Maniwa, Yutaka; Kataura, Hiromichi; Abe, Masatoshi; Fujiwara, Akihiko; Fujiwara, Ryuji; Kira, Hiroshi; Tou, Hideki; Suzuki, Shinzo; Achiba, Yohji; Nishibori, Eiji; Takata, Masaki; Sakata, Makoto; Suematsu, Hiroyoshi			
Citation	Journal of the Physical Society of Japan, 72(1): 45–48			
Issue Date	2003			
Туре	Journal Article			
Text version	author			
URL	http://hdl.handle.net/10119/4750			
Rights	This is the author's version of the work. It is posted here by permission of The Physical Society of Japan. Copyright (C) 2003 The Physical Society of Japan. Yutaka Maniwa, Hiromichi Kataura, Masatoshi Abe, Akihiko Fujiwara, Ryuji Fujiwara, Hiroshi Kira, Hideki Tou, Shinzo Suzuki, Yohji Achiba, Eiji Nishibori, Masaki Takata, Makoto Sakata and Hiroyoshi Suematsu, Journal of the Physical Society of Japan, 72(1), 2003, 45-48. http://jpsj.ipap.jp/link?JPSJ/72/45/			
Description				



C_{70} Molecular Stumbling inside Single-Walled Carbon

Nanotubes

Yutaka MANIWA^{1,6,*}, Hiromichi KATAURA¹, Masatoshi ABE¹, Akihiko FUJIWARA^{2,6}, Ryuji FUJIWARA¹, Hiroshi KIRA¹, Hideki TOU¹, Shinzo SUZUKI³, Yohji ACHIBA³, Eiji NISHIBORI⁴, Masaki TAKATA⁴, Makoto SAKATA⁴ and Hiroyoshi SUEMATSU⁵

¹Department of Physics, Tokyo Metropolitan University, 1-1 Minamiosawa, Hachioji, Tokyo 192-0397 ²JAIST, Tatsunokuchi, Ishikawa 923-1292 ³Department of Chemistry, Tokyo Metropolitan University, 1-1 Minami-osawa, Hachioji, Tokyo 192-0397 ⁴Department of Applied Physics, Nagoya University, Nagoya 464-8603 ⁵SPring-8, 1-1-1 Kouto, Mikazuki-cho, Sayo-gun, Hyogo 679-5198 ⁶CREST, JST (Japan Science and Technology Corporation).

(Received August 27, 2002)

We report the structural study of C_{70} -one-dimensional (1D) crystal formed inside single-walled carbon nanotubes (SWNTs). X-ray diffraction measurements were performed between 100 K and 999 K on C_{70} -encapsulated SWNTs with an average diameter of 1.37 nm. Two different domains, where the dominant alignment of C_{70} molecular long axis is standing or lying with respect to the tube axis, were observed; the ratio of the standing to the lying C_{70} -domains is roughly 7:3. Thermal expansion of interfullerene distance gave no evidence for orientational phase transitions, not as in the 3D crystals. Instead, the long-range order of the standing C_{70} -alignment was thermally destroyed with an activation energy of 39 ± 4 meV. The results imply the importance of either the 1D fluctuation or the tube- C_{70} interaction at finite temperatures.

KEYWORDS: thermal expansion, carbon nanotube, SWNT, peapod, C₇₀, phase transition, structure, XRD, fullerene

Existence of nanometer-size inner hollow cavities^{1, 2} in singlewalled carbon nanotubes (SWNTs) encourages us to form onedimensional (1D) system. Recent efforts actually led to successful synthesis of high-quality fullerene crystals^{3, 4} inside SWNTs, the so called "peapods". Although several interesting properties⁵⁻¹⁰ have been predicted or observed in this system, order-disorder transition related to the orientation of fullerene molecule inside SWNTs has not yet been clarified. In the case of C_{60} -peapods, the theoretical calculation predicted that the electronic states near the Fermi level are substantially modified by the C_{60} -SWNT interaction⁵. Thus, in general, the issue of how the electronic state of peapods is affected by the fullerene orientation is an interesting one, and information on this is important for basic understanding of the physical properties of peapods. In the present paper, we report the structural study of C₇₀-peapods by means of X-ray diffraction (XRD) in a temperature range between 100 K and 999 K.

The peapods were prepared by a vapor reaction method^{4,6} using purified SWNTs. The starting raw materials were generated by a pulsed laser vaporization method using a carbon rod with Ni and Co catalysts¹¹. Transmission electron microscopy confirmed that the parallel-aligned carbon nanotubes were packed into bundles with a triangular lattice (Fig.1a). We also compared the results of C₇₀peapods with those of double-walled carbon nanotubes (DWNTs) and C₆₀-peapods. Here, the DWNTs were converted from C₆₀-peapods by heating at ~1470 K (ref. 12). The C₇₀ peapods and DWNTs are schematically illustrated in Figs. 1(b)-1(d).

Figure 2(a) shows the typical powder XRD patterns of C_{60} - and C_{70} -peapods and the pristine SWNTs at RT. The data were collected using synchrotron radiation with a wavelength of 0.1000 nm at beam lines BL02B2 of SPring-8 and BL1B of KEK PF. Samples were sealed in a quartz capillary after being evacuated at ~800 K to remove adsorbed gases¹³⁻¹⁵. The observed peaks are basically indexed on the basis of the 2D triangular lattice¹¹ formed by 1D SWNTs. In Fig. 2(a), we observed marked changes in the XRD profiles on

 $\mathbf{2}$

encapsulation: the 10 peak around $Q\sim4.5$ (1/nm) is strongly depressed, and its onset shifts to the high-Q side, consistent with earlier works on molecular encapsulation inside SWNTs (refs. 13-15). We also observed new peaks around Q=6 (1/nm), indicated by arrows. The lack of the corresponding peaks in the DWNTs (Fig. 2(c)) shows that they are assigned to diffraction peaks due to the 1D array of fullerene molecules inside. The estimated lattice constant, a, of the 1D fullerene crystals, which corresponds to the interfullerene distance, is shown in Table I, along with the interfullerene gap defined by g=a-M, where M is the mean diameter of the fullerene molecule.

The observed features mentioned above were well reproduced by a simulation (Fig. 2(b)), in which the SWNTs and fullerene molecules are approximated to homogeneously charged shells¹¹. Within the framework of this model, we cannot discuss the structures in detail, such as the carbon coordinates within a graphene sheet. However, we could obtain the average triangular lattice constant *L* and tube diameters *D*, and found that *L* and *D* almost retain on encapsulation: $L=1.649\pm0.010$ nm and $D=1.352\pm$ 0.002 nm for the C₆₀-peapods, and $L=1.683\pm0.010$ nm and $D=1.373\pm$ 0.002 nm for the C₇₀-peapods.

In the case of C_{70} peapods, the two types of interfullerene distances, corresponding to the two peaks shown by arrows in Fig. 2(a), were observed: 1.00 ± 0.01 nm and 1.10 ± 0.01 nm at RT. These distances nearly correspond to those for the so-called "standing" and "lying" alignments⁴ of the C_{70} molecules with an elongated "rugby-ball" shape, as schematically shown in Figs. 1(b) and 1(c), respectively. The observed clear double-peaked structure implies that there are two different domains; in one of them, the long molecular axes of C_{70} tend to align perpendicular to the tube axis at RT, but in the other, most C_{70} molecules align parallel to the tube axis. The simulation results indicate that the SWNTs for the standing alignment are dominant compared to those for the lying

alignment in the present sample, and the ratio of these domains is 7:3.

Because the SWNTs studied have a diameter distribution that peaks around ~1.37 nm (the mean diameter estimated from the present XRD profile), the mean gaps between the tube wall and C_{70} molecule is 0.29 nm for the standing alignment and 0.33 nm for the lying alignment. Interestingly, the former gap is nearly equal to 0.292 nm in the bulk crystal of solid C_{60} and to 0.29-0.31 nm in SWNT bundles. These findings suggest the importance of tube- C_{70} interaction in the stabilization of the standing alignment. The lying alignment may be favorable for thicker SWNTs, because the C_{70} molecules may tend to lie in order to gain the contact area between the tube wall and fullerene molecule. In thinner tubes, where the tube wall must be substantially deformed to insert the standing C_{70} , accommodation of the standing C_{70} is also difficult. Thus, the tube diameter is one of the important factors for determining the orientation of fullerene molecules inside the SWNTs. SWNTs with a different diameter actually gave a different standing alignment.

Now we discuss the thermal expansion of the C_{70} crystal. Figure 3 shows the temperature dependence of the interfullerene distance normalized at RT, along with that of solid C_{60} (shown by a solid straight line). We observed that the thermal expansion for the standing alignment is substantially larger, while that for the lying alignment is comparable to that of the bulk C_{60} crystal. This is unusual if the thermal expansion coefficient for the lattice constant, α_L , is dominated by that of the intermolecular gap, α_g . Assuming that the thermal expansion of the molecular axis is ignored, the α_g in the standing alignment is estimated to be ~11 x 10^{-5} (1/K) from the observed α_L as an average value between 300 K and 999 K, which is much larger than 2.6 x 10^{-5} (1/K) for the graphite interlayer gap, ~5.4 x 10^{-5} (1/K) for the solid C_{60} (ref. 16) and ~4.2 x 10^{-5} (1/K) for the SWNT bundles¹⁵.

Such a large thermal expansion of the standing alignment must be due to a reorientation of C_{70} molecules inside the tubes. In the case of 3D solid C_{70} , it has been known^{1,17} that the structural phase transition successively occurs at ~340 K and ~280 K: the C₇₀ molecules exhibit a quasi-free rotation above ~340 K, below which the molecular long axis freezes but the short axis is still dynamically disordered, and finally the complete freezing occurs below ~280 K. These orientational ordering transitions accompany a change in the lattice constant. In the present standing C_{70} peapods, almost all the molecules are aligned perpendicular to the tube axis at RT, so that when the T is raised from RT a jump of 2~3% in the lattice constant is expected at a transition into the "free-rotational state". The data, however, did not show such a sudden change. Instead, the lattice constant gradually increases with increasing T_{r} indicating that the C₇₀ molecular stumbling is thermally activated¹⁸.

Assuming the simplest model for a quantitative discussion, the lattice constant is given by

$$a = M_{s} + (1 + \alpha_{g}T)g(0) + (M_{L} - M_{s})\frac{\exp(-E_{0}/k_{B}T)}{\left[2 + \exp(-E_{0}/k_{B}T)\right]}$$
(1),

where $M_{\rm S}$, $M_{\rm L}$, g(0), and E_0 are the mean lengths of molecular short and long axes, intermolecular gap at T=0 K, and activation energy for molecular stumbling, respectively. The second term describes the thermal expansion of the intermolecular gap and the coefficient $\alpha_{\rm g}$ is taken to be ~5.4 x 10⁻⁵ (1/K), the value for the solid C₆₀. The third term is due to the C₇₀ stumbling, where E_0 is the energy required to make a C₇₀ molecule lie in the standing "ferromagnetic" array of molecules. (Note that the standing C₇₀ molecule can take two possible orientations perpendicular to the tube axis.) The least-squares fit with this equation leads to a good reproduction of the data, as shown by the thick solid curve in Fig. 3, using the parameters, $E_0=39\pm4$ meV and $g(0)=0.276\pm0.08$ nm.

Why is the long-range order of standing alignment gradually destroyed with increasing temperature? One possibility is the case that the C_{70} -intermolecular interaction is negligibly small and the standing alignment is stabilized solely by the tube- C_{70} interaction. In this case, the lying C_{70} should be thermally excited as observed. However, the fact that the transition temperatures (~280 K and ~340 K) in the bulk 3D crystals are comparable in magnitude to the observed $E_0/k_{\rm B}\sim449$ K suggests that the intermolecular interaction can not be ignored, because the transition temperature for the bulk materials is taken as a tentative magnitude for the intermolecular interaction. Thus, alternatively, the one dimensionality (1D) of the crystal must be considered. In 1D system with a short-range interaction¹⁹, it is known that the long-range order is destroyed by 1D fluctuation at finite temperatures. In 1D ising model with a ferromagnetic ground state, it is known that the domain-wall excitation is described by a similar formula to eq. (1). In the present case, however, since the lying and standing domains may have different energies, the situation is slightly different from the case of the above ising model. Here, we encounter a new situation where not only anisotropic $C_{70}-C_{70}$ interaction but also anisotropic C_{70} -SWNT interaction must be taken into account, and we need more sophisticated analysis for the lattice expansion.

Anyway, the present studies clarified that the standing alignment is dominant and stable at the low temperature in C_{70} peapods with typical SWNTs with a mean diameter of 1.37 nm. With increasing temperature, C_{70} stumbling is thermally activated with a rather small activation energy of 39 meV. Thus, in a broad temperature region including room temperature, the C_{70} molecular reorientation cannot be ignored, because it affects many basic physical properties of C_{70} -peapods. In the future, however, the molecular dynamics should be investigated as a function of the C_{70} filling inside the SWNTs, as well as a function of the diameter of SWNTs.

Acknowledgements

Authors thank Professor Y. Okabe for carefully reading the manuscript. This work was supported in part by a Grant-in-Aid for Scientific Research on the Priority Area "Fullerenes and Nanotubes" by the Ministry of Education, Culture, Sports, Science and Technology of Japan, and by a grant from Japan Society for Promotion of Science, Research for the Future Program. H. K is thankful for a Grant-in-Aid for Scientific Research (A), 13304026 by the Ministry of Education, Culture, Sports, Science and Technology of Japan.

References

 for example, Science of fullerenes and carbon nanotubes, eds
M.S. Dresselhaus, G. Dresselhaus and P.C. Eklund (Academic Press, New York, 1995).

2. S. Iijima: Nature 363(1993)603.

3. B.W. Smith, M. Monthioux and D.E. Luzzi: Nature 396(1998) 323.

4. H. Kataura, Y. Maniwa, T. Kodama, K. Kikuchi, H. Hirahara, K. Suenaga, S. Iijima, S. Suzuki, W. Kraetschmer and Y. Achiba: Proc. 25th Int. Conf. Phys. Semicond., Osaka, Japan, 2000, p. 1609.

5. S. Okada, S. Saito and A. Oshiyama: Phys. Rev. Lett. **86**(2001)3835.

6. H. Kataura, Y. Maniwa, T. Kodama, K. Kikuchi, H. Hirahara, K. Suenaga, S. Iijima, S. Suzuki, Y. Achiba and W. Kraetschmer: Synthetic Metals **121**(2001)1195.

7. H. Hirahara, K. Suenaga, S. Bandow, H. Kato, T. Okazaki, H. Shinohara and S. Iijima: Phys. Rev. Lett. **85**(2000)5384.

8. H. Hirahara, S. Bandow, K. Suenaga, H. Kato, T. Okazaki, H. Shinohara and S. Iijima: Phys. Rev. **B64**(2001)115420.

9. T. Pichler, H. Kuzmany, H. Kataura and Y. Achiba: Phys. Rev. Lett. 87(2001)267401.

10. X. Liu, T. Pichler, M. Knupfer, M. Golden, J. Fink, H. Kataura, Y. Achiba, K. Hirahara and S. Iijima: Phys. Rev. B 65(2002)045419.

11. A. Thess, R. Lee, P. Nikolaev, H. Dai, P. Petit, J. Robert, C. Xu, Y.H. Lee, S.G. Kim, A.G. Rinzler, D.T. Colbert, G.E. Scuseria, D. Tomanek, J.E. Fischer and R.E. Smally: Science 273 (1996)483.

12. S. Bandow, M. Takizawa, H. Hirahara, M. Yudasaka and S. Iijima: Chem. Phys. Lett. **337**(2001)48.

13. Y. Maniwa, Y. Kumazawa, Y. Saito, H. Tou, H. Kataura, H. Ishii, S. Suzuki, Y. Achiba, A. Fujiwara and H. Suematsu: Jpn. J. Appl. Phys. 38(1999)L668.

14. A. Fujiwara, K. Ishii, H. Suematsu, H. Kataura, Y. Maniwa, S. Suzuki and Y. Achiba: Chem. Phys. Lett. **336**(2001)205.

15. Y. Maniwa, R. Fujiwara, H. Kira, H. Tou, H. Kataura, S. Suzuki, Y. Achiba, E. Nishibori, M. Takata, M. Sakata, A. Fujiwara and H. Suematsu: Phys. Rev. **B64**(2001)241402(R).

16. W.I.F. David, R.M. Ibberson, T.J.S. Dennis, J.P. Hare and K. Prassides: Europhys. Lett. **18**(1992)219.

17. G.B.M. Vaughan, P.A. Heiney, J.E. Fischer, D.E. Luzzi, D.A. Ricketts-Foot, A.R. McGhie, Y-W. Hui, A.L. Smith, D.E. Cox, W.J. Romanow, B.H. Allen, N. Coustel, J.P. McCauley Jr. and A.B. Smith III: Science **254**(1991)1350.

18. If the phase transition is first-order but there is a distribution of the transition temperature, we would observe a new peak slightly shifted from the two peaks observed. This new peak must grow with increasing temperature.

19. *Statistical Physics*, eds L.D. Landau and E.M. Lifshitz, (Butterworth-Heinemann, 1980).



Figure 1. (a) An example of transmission electron microscopy (TEM) image of C_{70} -peapods. (b), (c) and (d) Schematic illustrations of C_{70} standing alignment, lying alignment, and double-wall carbon nanotube (DWNT), respectively. The DWNT has a (10, 10) index for the outer tube, and (5, 5) for the inner tube. The inset shows a cross section of a bundle. The scale is 10 nm.



Figure 2. XRD profiles of pristine (empty) SWNTs, C_{70} -peapods and C_{60} -peapods: (a) observed and (b) simulated. In the simulations, a small amount of bundles of empty SWNTs was assumed to be included: 15 wt% for the C_{60} -peapods and 30 wt% for the C_{70} -peapods. (c) Observed XRD profile of DWNTs. The arrow shows the lack of the peak due to 1D C_{60} crystal observed in C_{60} -peapods.



Figure 3. Normalized interfullerene distance (1D lattice constant) as a function of temperature. The solid straight line shows that of solid C_{60} . The solid curve is the least-squares fit with eq. (1) in the text.

Table I. Interfullerene distance (lattice constant), interfullerene gap and tube-fullerene gap estimated by XRD analysis.

			[nm]
	Interfullerene	Interfullerene	fullerene-
	distance, a	gap*, g	tube gap**
C ₆₀ -peapod (#1)	0.97	0.26	0.321
(#2)	0.95 (0.95***)	0.24	0.321
C ₇₀ -peapod	1.00 (1.00***)	0.290	0.289
	1.10 (1.10***)	0.304	0.332
C ₆₀ solid ^{****}	1.002		0.292

*The molecular shape is assumed to be spherical with a mean diameter of 0.710 nm for C_{60} and that of a rugby ball with a mean short (a-b) axis of 0.712 nm and a mean long (c-) axis of 0.796 nm for C_{70} (ref. 1).

**The gap between the tube wall and fullerene molecules estimated using the average tube diameter.

*** From electron diffraction measurements (ref. 4).

**** Reference 1.